

DECLARATION OF PROPERTIES NO. 1393-CPR-0918

NOVATOP STATIC

Identification code:	SWP 60 (local spruce).
Type:	Multilayer solid wood panel SWP/1 NS, SWP/1 SD according to EN13353.
Intended use:	Used for bearing and non-bearing panels in the building industry, for indoor or outdoor use and fire resistance class D.
Manufacturer:	AGROP NOVA a.s., Ptenský Dvorek 99, CZ-798 43 Ptení, Tax ID: CZ26243237
Assessment and verification procedures:	The system of assessment 2+ The manufacturer performs: <ol style="list-style-type: none">determination of the product type on the basis of the type testing (including sampling). Computation for the type, tabular values or descriptive documentation of the product,factory production control,testing of samples taken at the factory in accordance with the prescribed test plan. The notified body for production control certification issues a certificate of conformity of production control based on: <ol style="list-style-type: none">the initial inspection of the factory and of the factory production control,the continuous surveillance, assessment and approval of the factory production control.
The notified body:	Timber Research and Development Institute Prague s.p. performed the initial inspection of the factory and of the factory production control and performs the continuous surveillance, assessment and approval of the factory production control (system 2 + according to ZA-norm) and issued a Certificate of factory production control No. 1393-CPR-0918 according to ZA-norm EN 13986:2004.

Basic characteristics	Property	Harmonized technical specifications
Density	490 kg/m ³	EN 13986:2004
Reaction to fire	D-s2, D0 according to EN13 501-1	EN 13986:2004
Design value of thermal conductivity (λ)	0,13 W/mK according to EN ISO 10456	EN 13986:2004
Factor of diffusion resistance (μ)	200/70 (dry/wet) according to EN ISO 10456	EN 13986:2004
Sound absorption	250–500 Hz – 0,1 1000–2000 Hz – 0,3	EN 13986:2004
Airborne sound insulation (dB)	$R = 13 \times \log(m_a) + 14$ m_a = surface weight kg/m ²	EN 13986:2004
Specific thermal capacity (c_p)	1600 J/kgK according to EN ISO 10456	EN 13986:2004

MECHANICAL PROPERTIES

Property		Testing method	Thickness [mm]	
			45 (9-9-9-9-9)	60 (9-9-24-9-9)
ρ	Density (kg/m ³)	EN 323	420	420
Characteristic bending strength perpendicular to the panel plane [N/mm ²] $f_{m,k}$				
$f_{m,0,k}$	Bending strength parallel to the fibres of the outer layers	EN 789	48	35
$f_{m,90,k}$	Bending strength perpendicular to the fibres of the outer layers	EN 789	3,3	6
Characteristic value of the modulus of elasticity perpendicular to the panel plane [N/mm ²] $E_{m,mean}$				
$E_{m,0}$	Modulus of elasticity parallel to the fibres of the outer layers	EN 789	10300	10400
$E_{m,90}$	Modulus of elasticity perpendicular to the fibres of the outer layers	EN 789	320	1000

The product properties are in compliance with the properties listed in the table.

This Declaration of Properties is issued under the sole responsibility of the manufacturer.

Signed for and on behalf of the manufacturer:

NOVATOP 

AGROP NOVA a.s.
 Ptenský Dvůrek 99 • 798 43 Ptení
 IČ: 26243237 • DIČ: CZ26243237 

Ing. Radek Oslizlo
 CTO

1. 1. 2025

DECLARATION OF PROPERTIES NO. 1393-CPR-0921

NOVATOP STATIC

Identification code:	SWP 60 (local spruce).
Type:	Multilayer solid wood panel SWP/2 NS, SWP/2 SD according to EN13353.
Intended use:	Used for bearing and non-bearing panels in the building industry, for indoor or outdoor use and fire resistance class D.
Manufacturer:	AGROP NOVA a.s., Ptenický Dvůrek 99, CZ-798 43 Ptení, Tax ID: CZ26243237
Assessment and verification procedures:	The system of assessment 2+ The manufacturer performs: <ol style="list-style-type: none">determination of the product type on the basis of the type testing (including sampling). Computation for the type, tabular values or descriptive documentation of the product,factory production control,testing of samples taken at the factory in accordance with the prescribed test plan. The notified body for production control certification issues a certificate of conformity of production control based on: <ol style="list-style-type: none">the initial inspection of the factory and of the factory production control,the continuous surveillance, assessment and approval of the factory production control.
The notified body:	Timber Research and Development Institute Prague s.p. performed the initial inspection of the factory and of the factory production control and performs the continuous surveillance, assessment and approval of the factory production control (system 2 + according to ZA-norm) and issued a Certificate of factory production control No. 1393-CPR-0921 according to ZA-norm EN 13986:2004.

Basic characteristics	Property	Harmonized technical specifications
Density	490 kg/m ³	EN 13986:2004
Reaction to fire	D-s2, D0 according to EN13 501-1	EN 13986:2004
Design value of thermal conductivity (λ)	0,13 W/mK according to EN ISO 10456	EN 13986:2004
Factor of diffusion resistance (μ)	200/70 (dry/wet) according to EN ISO 10456	EN 13986:2004
Sound absorption	250–500 Hz – 0,1 1000–2000 Hz – 0,3	EN 13986:2004
Airborne sound insulation (dB)	$R = 13 \times \log(m_a) + 14$ m_a = surface weight kg/m ²	EN 13986:2004
Specific thermal capacity (c_p)	1600 J/kgK according to EN ISO 10456	EN 13986:2004

MECHANICAL PROPERTIES

Property		Testing method	Thickness [mm]	
			45 (9-9-9-9-9)	60 (9-9-24-9-9)
ρ	Density (kg/m ³)	EN 323	420	420
Characteristic bending strength perpendicular to the panel plane [N/mm ²] $f_{m,k}$				
$f_{m,0,k}$	Bending strength parallel to the fibres of the outer layers	EN 789	48	35
$f_{m,90,k}$	Bending strength perpendicular to the fibres of the outer layers	EN 789	3,3	6
Characteristic value of the modulus of elasticity perpendicular to the panel plane [N/mm ²] $E_{m,mean}$				
$E_{m,0}$	Modulus of elasticity parallel to the fibres of the outer layers	EN 789	10300	10400
$E_{m,90}$	Modulus of elasticity perpendicular to the fibres of the outer layers	EN 789	320	1000

The product properties are in compliance with the properties listed in the table.

This Declaration of Properties is issued under the sole responsibility of the manufacturer.

Signed for and on behalf of the manufacturer:

NOVATOP 
 AGROP NOVA a.s.
 Ptenský Dvůrek 99 • 798 43 Ptení
 IČ: 26243237 • DIČ: CZ26243237 

Ing. Radek Oslizlo
 CTO

1. 1. 2025